

Document	RY-TDS-704
Revision	Rev. 1.0
Issue date	July 2026
Status	Issued

[object Object]

[object Object] · [object Object]

1. PRODUCT DESCRIPTION

Rayson UraForce WB60 is a two-component, water-based aliphatic polyurethane dispersion clear coat, crosslinked with a solvent-free hardener, giving a non-yellowing, abrasion-resistant finish in gloss, satin or matt.

UraForce WB60 is the water-based clear coat of the UraForce family. The aliphatic polyurethane dispersion crosslinks with a solvent-free hardener into a non-yellowing film with excellent abrasion resistance, low dirt pick-up and good water repellence — pencil hardness above H and gloss of 85 at 60° in the gloss grade.

2. RECOMMENDED USES

- UV-resistant clear sealing of concrete floors
- Topcoat finishes on hard surfaces such as stone and limestone
- Hygienic coatings for walls and floors
- Non-yellowing protective finishes in occupied commercial interiors

4. KEY PROPERTIES

- Low VOC, low odour — suited to occupied buildings
- Non-yellowing aliphatic PU clear coat in gloss, satin or matt
- Excellent abrasion resistance and low dirt pick-up
- Solvent-free hardener system
- uv stability
- abrasion resistance
- low odour
- hygiene

3. SUITABLE SUBSTRATES

- Mechanically prepared concrete (minimum 28 days old, moisture content below 5%)
- Metal (prepared)
- Stone and limestone
- Walls and floors

5. SYSTEM ROLE

finish.




Figure 1 — Typical system build-up (top to bottom). Layer thicknesses are system-dependent; confirm the specification for your project.

6. TECHNICAL DATA

Surface preparation	[object Object]
Mixing / dilution	[object Object]
Application method	Short-bristled brush, Roller
Coverage	Available from the Rayson technical team on request.
Application conditions	[object Object]
Drying & curing	[object Object]
Recoat interval	[object Object]
Film / thickness	[object Object]
Pack sizes	[object Object]

Storage	[object Object]
Shelf life	[object Object]

7. APPLICATION WORKFLOW



Figure 2 — Application workflow. Each stage is a hold point: confirm the previous stage is complete and within specification before proceeding.

8. RECOMMENDED SYSTEM

Clear low-odour floor seal

- 1. Prepare the substrate mechanically and vacuum clean
- 2. Apply minimum 2 coats of Rayson UraForce WB60, stripe-coating edges by brush

9. LIMITATIONS

- Minimum substrate temperature 5 °C; minimum mixing temperature 10 °C; minimum curing temperature 5 °C
- Mixed material must be used within its pot life; cures faster in hot weather and in large batches
- Hardener has a shorter shelf life than the base — store sealed and dry
- Clear coat — substrate appearance and defects show through

10. HEALTH & SAFETY

[object Object]

DISCLAIMER

The information in this data sheet is given in good faith and reflects typical values and general good practice. Because site conditions and workmanship are beyond our control, Rayson gives no warranty implied from this document; users should verify suitability for their specific application and confirm they are working from the current issue. For project-specific advice, contact the Rayson technical team.

RAYSON HIGH PERFORMANCE COATINGS

Singapore
Tel / WhatsApp: +65 9821 9129
samuelpacx@hotmail.com

Product page:
<https://rayson.sparcoasia.com/products/uraforce-wb60/>